

TEST REPORT



Page 1 of 3

REPORT NUMBER :	TURT180062502
APPLICANT NAME :	Leba San. Ürünl. İth. ve İhr. Paz. A.Ş.
ADDRESS :	GEPOSB Cumhuriyet Cad. 4053 Ada 20 Parsel No:5 Gebze Kocaeli / TÜRKİYE TEL:0262 751 23 48 FAX:0262 751 23 46
Attention :	Ali Kemal Kamer (alikemal@leba.com.tr)
SAMPLE DESCRIPTION :	See attachment
DATE IN :	30 March ,2018 (10:56:00)
DATE OUT :	10 April ,2018
COUNTRY OF ORIGIN :	TURKEY
REQUEST.	RoHS Test was performed according to 2011/65/EU Directive.
RESULTS:	See attachment

		CONCLUSION
PART	DESCRIPTION	
Sample 1	D.O.T.P(LbSoft33) Liquid item	Pass
Sample 2	D.O.A. Liquid item	Pass
Sample 3	T.O.T.M. Liquid item	Pass

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at http://www.intertek.com/terms. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and TÜRKAK accreditation requirements. Unless otherwise is specified, all Pass or Fail results need to be re-tested to determine their disposition up to customer's decision. Opinions and interpretations expressed herein are outside the scope of TÜRKAK accreditation. Tests marked (*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory.

Volkan ALBAYRAK Customer Care Executive

Zeynep AKIN Chemical Laboratory Manager

Intertek Test Hizmetleri A.S. Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna-34197 /ISTANBUL Phone : +90 212 496 46 46 Fax: +90 212 452 80 55 e-mail : intertekcg.turkiye@intertek.com http://www.intertek-turkey.com

180062502

TEST REPORT

Interte Total Quality, Assured

REPORT : TURT180062502

		AB-0716-T	
10	April	,201	8

Page 2 of 3

(A) TEST RESULT SUMMARY ACCORDING TO IEC 62321

Electrotechnical Products-Determination of Levels of Six Regulated Substances

TESTING ITEM		RESULT		
	Sample 1	Sample 2	Sample 3	
	Part	Part	Part	
Cadmium (Cd) Content	ND	ND	ND	
Chromium VI (Cr+6) Content (ppm) (for non- metal)	ND	ND	ND	
Chromium VI (Cr+6) Content (µg/cm²) (for metal)	NA	NA	NA	
Lead (Pb) Content	ND	ND	ND	
Mercury (Hg) Content	ND	ND	ND	
Flame Retardants				
Polybrominated Biphenyls (PBB)	NA	NA	NA	
Monobromobiphenyl (MonoBB)	NA	NA	NA	
Dibromobiphenyl (DiBB)	NA	NA	NA	
Tribromobiphenyl (TriBB)	NA	NA	NA	
Tetrabromobiphenyl (TetraBB)	NA	NA	NA	
Pentabromobiphenyl (PentaBB)	NA	NA	NA	
Hexabromobiphenyl (HexaBB)	NA	NA	NA	
Heptabromobiphenyl (HeptaBB)	NA	NA	NA	
Octabromobiphenyl (OctaBB)	NA	NA	NA	
Nonabromobiphenyl (NonaBB)	NA	NA	NA	
Decabromobiphenyl (DecaBB)	NA	NA	NA	
Polybrominated Diphenyl Ethers (PBDE)	NA	NA	NA	
Monobromodiphenyl Ether (MonoBDE)	NA	NA	NA	
Dibromodiphenyl Ether (DiBDE)	NA	NA	NA	
Tribromodiphenyl Ether (TriBDE)	NA	NA	NA	
Tetrabromodiphenyl Ether (TetraBDE)	NA	NA	NA	
Pentabromodiphenyl Ether (PentaBDE)	NA	NA	NA	
Hexabromodiphenyl Ether (HexaBDE)	NA	NA	NA	
Heptabromodiphenyl Ether (HeptaBDE)	NA	NA	NA	
Octabromodiphenyl Ether (OctaBDE)	NA	NA	NA	
Nonabromodiphenyl Ether (NonaBDE)	NA	NA	NA	
Decabromodiphenyl Ether (DecaBDE)	NA	NA	NA	

Remarks : ppm=Parts per million based on dry weight of sample µg/cm²=Microgram per square centimetre mg/kg with 50 cm²=Milligram per kilogram with 50 square centimetre ND =Not detectedNA =Not applicableNR =Not requested Estimated Total Uncertanity= ((Heavy Metal: ±7%, PBB/PBDE: ±6%))

> Intertek Test Hizmetleri A.S. Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna-34197 /ISTANBUL Phone : +90 212 496 46 46 Fax: +90 212 452 80 55 e-mail : intertekcg.turkiye@intertek.com http://www.intertek-turkey.com

intertek Total Quality. Assured.

TEST REPORT

REPORT : TURT180062502

(B) REQUIREMENT:

SUBSTANCE	LIMITS	
Cadmium (Cd) Content	0.01 % (100 ppm)	
Chromium VI (Cr+6) Content (ppm) (for non metal)	0.1 % (1000 ppm)	
Chromium VI	<u>Colorimetric</u> <u>result</u>	<u>Qualitative</u> <u>Result</u>
(Cr+6) Content (µg/cm ²) (for metal)	< 0.10 µg/cm ² ≥ 0.10 µg/cm ² and ≤ 0.13 µg/cm ² > 0.13 µg/cm ²	Negative Inconclusive Positive
Lead (Pb) Content	0.1 % (1000 ppm)	
Mercury (Hg) Content	0.1 % (1000 ppm)	
Flame Retardants	0.1 % (1000 ppm)	

(C) TEST METHOD :

Testing Item	Testing Method	Reporting Limit
Cadmium (Cd)Content	With reference to IEC 62321- 5:2013,by microwave or acid digestion and determined by ICP-OES	Plastic : 2.5 ppm, Metal : 5 ppm, Seramic : 1.25 ppm
Lead (Pb)Content	With reference to IEC 62321- 5:2013,by microwave or acid digestion and determined by ICP-OES	Plastic : 5 ppm, Metal : 10 ppm, Seramic : 2.5 ppm
Mercury (Hg)Content	With reference to IEC 62321- 4:2017,by microwave or acid digestion and determined by ICP-OES	Plastic : 5 ppm, Metal : 10 ppm, Seramic : 2.5 ppm
Chromium VI (Cr6+) (For non-metal)	With reference to IEC 62321-7- 2:2017,by alkaline digestion and determined by UV-VIS spectrophotometer	Plastic : 25 ppm (PVC based) /8.33 ppm (other), Seramic : 8.33 ppm
Chromium VI (Cr6+) (For metal)	With reference to IEC 62321-7- 1:2015 ,by boiling water extraction and determined by UV-VIS spectrophotometer	0.1 mg/kg with 50 cm ² (IN TESTING SOLUTION)
PBBs/PBDEs	With reference to IEC 62321- 6:2015,by solvent extraction and determined by GC/MS and HPLC	5 ppm

END OF TEST REPORT



Page 3 of 3