


D. O. A.

DI 2-ETHYLHEXYL ADIPATE



D.O.A. is generally used for its low temperature characteristics. It is highly compatible with PVC, rubber and nitro cellulose. It is generally used for food contact applications for health concerns. D.O.A. is chemically stable and resistant to discoloration on extended exposure to heat. It can also be used in plastisols for its good solvating properties.

PROPERTIES	VALUE	UNIT
Density (20°C)	0,924-0,926	gr/cm ³
Refractive Index (20°C)	1,446-1,448	
Acidity	0,1 Max.	mgKOH/g
Viscosity (20°C)	13-15	mPa.s
Flash Point	> 210	°C
Ester Content	99,5	%
Water Content	0,05 Max.	%
Colour	20 Max.	Hazen
Cas No	103-23-1	
EC No	203-090-1	

